



Technical Data Sheet

RAL 7037 Dusty Grey PLSF 70184

Description:	<i>PLSF70184, RAL 7037 (Dusty Grey)</i> is thermosetting Polyester TGIC powder coating and is designed for interior or exterior applications.	
Typical Applications:	General metals, architectural, automotive, lawn & garden furniture, stadium seating, light fixtures, marine, fencing, etc.	
Typical Physical Properties:	Film Thickness	2.0-3.5 mil
	Gloss 60°angle (ASTM D-523-89)	80+
	Hardness (ASTM D-3363-92A)	H – 2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs
	Salt Spray (ASTM B117)	1000 hrs, < 3mm creep
	Specific Gravity (calculated)	1.60±0.03
Application Data:	<i>PLSF70184, RAL 7037 (Dusty Grey)</i> is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 K.	
Cure Schedule:	<i>PLSF70184, RAL 7037 (Dusty Grey)</i> can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable. Standard Cure: 10 Minutes @ 340°F Peak Metal Temperature	
Storage:	<i>PLSF70184, RAL 7037 (Dusty Grey)</i> should be stored at temperatures below 80 ⁰ f, in a dry area away from any heat source.	
Notes:	All tests were performed on Bond rite 1000, iron phosphated panels with a nominal film thickness of 2-3 mils. Please refer to the MSDS for safety information.	

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

3601 North Interstate 35
Gainesville
Texas 76240
Tel. (940) 668 1062
Fax. (940) 668 1061
www.ifscos.com Email: info@ifscos.com