



Technical Data Sheet

URSS 90072 OB Gold

Description: Thermosetting polyurethane powder coating.

Typical Applications: Decorative

Typical Physical Properties:	Film Thickness (ASTM D)	2.5+ mil
	Gloss (visual)	Semi
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5b (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160 in-lbs
	Salt Spray (ASTM B117)	1000 Hrs < 1/8"
	Specific Gravity	1.56

Application Data: Polyurethane's are to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kv.

Cure Schedules: Polyurethane's can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 12 Minutes @ 400°F Peak Metal Temperature

Storage: Product should be stored at temperatures below 80°F, in a dry area away from any heat source.

Notes: All tests were performed on Bonderite 1000, iron phosphated panels with a nominal film thickness of 2 mils.

Lower gloss levels may require higher cure temperatures or longer dwell times.
Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

3601 North Interstate 35
Gainesville
Texas 76240
Tel. (940) 668 1062
Fax. (940) 668 1061

www.ifscos.com Email: info@ifscos.com